



RoofDek® D159 Perforated



SECTION THROUGH PROFILE

PERFORATIONS 3.3 Diameter Holes on 6.0 Triangular Pitch



Gauge (mm)	Substrate	Available Coating Type			Minimum Length (mm)	Maximum Length (mm)
		Zinc*	MagiZinc®**	Colorcoat® PE15***		
1.25	Steel	Z 275	MZ 140	Interior Liner PE15	500	12000
1.50	Aluminium	Mill		White ARS	500	12000

* Zinc (Z) Coating only, minimum coating weight 275g/m2 (total for both sides).

** MagiZinc® MZ (ZM Zinc-Magnesium-Aluminium) Coating only, minimum coating weight 140g/m2 (total for both sides).

*** Colorcoat® PE15 uses Z 275 coated substrate.

**** Colorcoat HPS 200 Ultra® (ZA Zinc-Aluminium) Galvalloy® 255g/m2

Zinc, MagiZinc® and Colorcoat® PE15 coated products use 280MPa yield substrate. Colorcoat HPS 200 Ultra® coated product uses 220MPa substrate.

NOTE:

RoofDek®, Colorcoat®, HPS 200 Ultra® and MagiZinc® are registered trademarks of Tata Steel UK Limited.

All dimensions are to the intersections of profile elements and are measured in millimetres unless stated otherwise.

Manufactured to BS EN 10346

TATA STEEL

Tata Steel UK Limited retain the right to amend the construction and technical specifications shown on this drawing without prior notice.

SALES AND TECHNICAL OFFICE

Tata Steel
Building Systems UK
Shotton Works
Deeside
Flintshire
CH5 2NH

TEL: 01244 89 2199

www.tatasteelconstruction.com

Title:

**RoofDek® D159
Perforated**

Scale:

1:5 @ A4

© Tata Steel UK Ltd.

Dwg. No.

TS-001-D159 P

Rev.

01